

U.S. Patent Application No. 10/620,269
Amendment dated October 25, 2007

RECEIVED
CENTRAL FAX CENTER
OCT 25 2007

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently amended) A carbon black having an I₂ No. of from about 50 to about 112 mg/g as measured by ASTM D1510, primary particle size of not greater than 25 nm as measured by ASTM D3849-89, and at least the following properties:

- a) an ash content of less than about 1% as measured by ASTM D-1506;
- b) a total sulfur content of less than about 2% as measured by ASTM D-1619; and
- c) a 325 mesh residue of about ~~200 ppm or less~~ less than 20 ppm as measured by ASTM D-1514.

2. (Original) The carbon black of claim 1 wherein I₂ No. is 73-104 mg/g.

3. (Original) The carbon black of claim 2 wherein the I₂ No. is 75-99 mg/g.

4. (Original) A polymer composition comprising at least one polymer and the carbon black of claim 1.

5. (Original) The polymer composition of claim 4 wherein the I₂ No. of the carbon black is 73-104 mg/g.

6. (Original) The polymer composition of claim 4 wherein the I₂ No. of the carbon black is 75-99 mg/g.

7. (Original) The polymer composition of claim 4 wherein the polymer composition comprises 0.5 to 300 parts by weight carbon black per 100 parts by weight of polymer.

8. (Original) The polymer composition of claim 4 wherein the polymer composition comprises 0.5 to 100 parts by weight carbon black per 100 parts by weight of polymer.

U.S. Patent Application No. 10/620,269
Amendment dated October 25, 2007

9. (Original) The polymer composition of claim 4 wherein the polymer composition comprises 0.5 to 80 parts by weight carbon black per 100 parts by weight of polymer.

10. (Original) The polymer composition of claim 4 wherein the polymer is a polyethylene or copolymers thereof.

11. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 104 mg/g and the primary particle size is approximately 16 nm.

12. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 89 mg/g and the primary particle size is approximately 18 nm.

13. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 91 mg/g and the primary particle size is approximately 18 nm.

14. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 99 mg/g and the primary particle size is approximately 17 nm.

15. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 86 mg/g and the primary particle size is approximately 19 nm.

16. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 96 mg/g and the primary particle size is approximately 17 nm.

17. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 85 mg/g and the primary particle size is approximately 17 nm.

18. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 73 mg/g and the primary particle size is approximately 18 nm.

19. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 86 mg/g and the primary particle size is approximately 19.5 nm.

20. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 90 mg/g and the primary particle size is approximately 19 nm.

U.S. Patent Application No. 10/620,269
Amendment dated October 25, 2007

21. (Original) The carbon black of claim 1 wherein the I₂ No. is approximately 89 mg/g and the primary particle size is approximately 17 nm.

22-23. (Canceled)

24. (Original) The carbon black of claim 1, wherein said total sulfur content is less than about 0.1%.

25. (Canceled)

26. (Original) The polymer composition of claim 4, wherein said polymer is a polyolefin.

27. (Original) The polymer composition of claim 4, wherein said polymer comprises LLDPE, HDPE, MDPE, or combinations thereof.

28. (Original) The polymer composition of claim 4, wherein said polymer comprises a polystyrene, polycarbonate, nylon, or combinations thereof or copolymers thereof.

29. (Original) An article comprising the polymer composition of claim 4.

30. (Original) The article of claim 29, wherein said article is a pipe, connector, cable jacketing, membrane, molding, or components thereof.

31. (Original) The article of claim 29, wherein said article is a pressure pipe.

32. (Original) The article of claim 29, wherein said pressure pipe is a UV pressure pipe.

33. (Original) The article of claim 29, wherein said article is a potable water or gas pipe.

34. (Currently amended) The carbon black of claim 1, further comprising a CDBP of less than or equal to 102 cc/100 g, as measured by ASTM D3493-86.

35. (Original) The carbon black of claim 34 wherein the CDBP is 70-100 cc/100 g.

36. (Original) The carbon black of claim 34 wherein the CDBP is 80-95 cc/100 g.

U.S. Patent Application No. 10/620,269
Amendment dated October 25, 2007

37. (Currently amended) The carbon black of claim 1, having an I₂ No. of 50-85 mg/g; a primary particle size of less than or equal to 25 nm; and a CDBP of less than or equal to 96 cc/100 g, as measured by ASTM D3493-86.

38. (Original) The carbon black of claim 37 wherein the I₂ No. is 55-80 mg/g.

39. (Original) The carbon black of claim 37 wherein the primary particle size is from greater than 20 nm to 25 nm.

40. (Original) The carbon black of claim 37 wherein the CDBP is 50-96 cc/100 g.

41. (Original) The carbon black of claim 32 wherein the I₂ No. is 60-78 mg/g.